

Plasma-Activated Electrolysis for Cogeneration of Nitric Oxide and Hydrogen from Water and Nitrogen

Hrishikesh Patel,^{†,§} Rakesh K. Sharma,^{†,§} Vasileios Kyriakou,[†] Arunkumar Pandiyan,[†] Stefan Welzel,[†] Mauritius C.M. van de Sanden,^{†,‡} and Mihalis N. Tsampas^{*,†}

[†]Dutch Institute for Fundamental Energy Research (DIFFER), De Zaale 20, 5612 AJ, Eindhoven, The Netherlands

[‡]Department of Applied Physics, Eindhoven University of Technology (TU.e), 5600 MB Eindhoven, The Netherlands

Supporting Information

ABSTRACT: With increasing global interest in renewable energy technology given the backdrop of climate change, storage of electrical energy has become particularly relevant. Most sustainable technologies (e.g., wind and solar) produce electricity intermittently. Thus, converting electrical energy and base molecules (i.e., H₂O, N₂) into energy-rich ones (e.g., H₂, NH₃) or chemical feedstock (e.g., NO) is of paramount importance. While H₂O splitting is compatible with renewable electricity, N2 fixation is currently dominated by thermally activated processes. In this work, we demonstrate an allelectric route for simultaneous NO and H₂ production. In our approach, H₂O is reduced to H₂ in the cathode of a solid oxide electrolyzer while NO is produced in the anode by the reaction of O^{2-} species (transported via the electrolyte) and plasma-activated N_2 species. High faradaic efficiencies up to 93% are achieved for NO



production at 650 °C, and NO concentration is >1000 times greater than the equilibrium concentration at the same temperature and pressure.

ne of the greatest challenges of our era is the substitution of fossil feedstock as energy sources with renewable energy sources. However, because of their intermittent nature and the harvesting in the form of electricity, their direct introduction into the value chain of, for example, chemical industry, remains challenging. Therefore, technologies based on renewable electricity that can transform base molecules (i.e., H₂O, N₂, CO₂) into energy- or chemicalrich molecules have attracted tremendous interest.¹⁻³ In the transition from low- to high-energy molecules or to valuable chemical feedstock (e.g., H₂, NH₃, CO, NO), the activation of chemical bonds (e.g., $N \equiv N$, O = C = O) is a major issue that has to be addressed.¹

Among the three base molecules, N2 is by far the least reactive because the N≡N triple bond is very strong and difficult to activate because of the absence of a permanent dipole.⁴ Consequently, even with the best available catalysts, a substantial energy input is required to activate N2. At the industrial level, nitrogen fixation is realized via ammonia and nitric oxide synthesis.5-8

In the Haber-Bosch (HB) synthesis of ammonia, heterogeneous Fe- or Ru-based catalysts are used at temperatures from 400 to 500 °C in order to cleave the N≡N bond and convert N2 and H2 to NH3 at realistic rates. In this temperature range, the NH₃ yield is very low at atmospheric pressure because of thermodynamic limitations, and thus, HB synthesis is carried out at 100-250 bar for shifting the equilibrium toward ammonia synthesis.⁵ For a fully optimized and integrated HB process, energy efficiencies as low as 0.48 MJ/N-mol are reported.⁵

 N_2 fixation can also occur in the form of nitric oxide (NO), which is a valuable chemical feedstock because of its commercial relevance especially for use in fertilizers, synthetic fibers, and plastics and in drugs for cancer or inflammatory disorders.⁷⁻¹⁰ NO is an intermediate in the industrial production of nitric acid, one of the basic industrial chemicals with annual world production of about 60 million metric ton/ year.10

Most of today's synthetic NO is made by oxidizing ammonia, while NO formation in N2 and O2 atmosphere takes place at high temperatures (>2000 °C).^{7,8} Both processes are based on thermal catalysis with a significant CO₂ footprint,

Received: July 15, 2019 Accepted: August 8, 2019



Figure 1. Schematic representation of hybrid plasma-activated solid oxide electrolyte cell (SOEC) reactor setup.



Figure 2. Operation principles of conventional (left) and activated (right) SOEC electrolysis.

and thus, electrification of $\rm N_2$ fixation is highly desirable and remains one of the biggest challenges.

Gas discharges are electrically driven processes and are easy to combine with intermittent electricity because of their fast response times. A gas discharge (plasma) is an ionized gas and represents a reactive environment due to the presence of charges, excited species, and radicals. Plasmas are reported as one of the most promising approaches for the activation of the $N\equiv N$ bond.^{11–14} Particularly, nitrogen plasmas produced by high or radio frequency (RF) sources at reduced pressures are well-known for efficiently producing vibrationally excited molecules which further dissociate into atomic nitrogen.^{15–17} The relative concentration of the latter species in the afterglow of the plasma might be as high as 1000 ppm.¹⁷

Plasma-based processes have gained a great deal of attention for N₂ fixation, starting from the oldest electric arc-based Birkeland–Edye process¹⁸ to different types of plasmas and reactor configurations.^{19–23} Moreover, the combination of gas discharges with catalytic materials has been studied and reported for various catalysts and catalyst supports.^{24–29} In the same context, the tremendous enabling potential of (e.g., nitrogen) plasmas in combination with poor activity catalysts in conventional thermal catalysis has been demonstrated.^{13,29} Recently, the combination of a plasma with aqueous or polymer electrolyte-based electrochemical systems has been reported.^{30,31} Nevertheless, to the best of our knowledge no such effort has been attempted for NO synthesis by N₂ and H₂O.

In this work, we demonstrate a novel approach for the cogeneration of NO and H_2 from H_2O and plasma-activated N_2 gas using a hybrid plasma-activated solid oxide electrolysis cell (SOEC). The novelty is related to the fact that the plasma-activated nitrogen species are generated separately from the oxygen species: the oxygen to form NO is provided only through solid oxide membrane contacting the downstream part

of an N₂ plasma. The oxygen ions permeating the membrane is produced during water reduction to H₂ in the cathodic compartment (which is isolated from the anodic one with a tubular electrolyte membrane). This setup therefore cogenerates the products, NO and H₂, in an integrated electrically driven way in two isolated compartments, i.e. NO in the plasma compartment and H₂ in the inner compartment (cf. Figure 1 for details). The main focus of the work is in the NO production; however, it is worthwhile to note that hydrogen is also a commercially viable compound in addition to being a topic of research for the hydrogen economy. Also note that the separation of the products (NO and H₂) from their corresponding gas streams, i.e., N₂ and H₂O, respectively, can be easily realized nowadays by standard processes (i.e., adsorption and condensation³²).

Our hybrid reactor (Figure 1) consists of an inductive coil which is connected to the matching network of a RF power supply. The coil encloses a quartz tube that is mounted on both ends to two vacuum flanges. These flanges serve as mechanical support for both the quartz tube and the tubular solid oxide electrolysis cell (SOEC) and provide electrode connections with the external circuit. In what follows we refer to the inner volume of the tubular SOEC as inner compartment while the active and passive zone of the plasma in the quartz tube is referred to as plasma compartment. The reactor is equipped with two inlets (for H_2O and N_2) and two outlets, one for each compartment (Figure 1). The SOEC is based on an oxygen ion conducting tubular membrane (made from yttria stabilized zirconia, YSZ) with one end closed on which porous Pt films (Figure S1) have been deposited on both sides of the tube. As depicted in the inset of Figure 1, the inner one serves as a cathode (counter-electrode) while the outer as an anode (plasma-electrode). H₂O is fed in the inner compartment (1 bar) of the tubular cell while N_2 is used as feed gas in the plasma compartment (5 mbar) where activation takes place by the RF plasma source.

Figure 2 depicts schematically the electrochemical reactions in each compartment under conventional and plasma-activated SOEC operation. In both cases water reduction to hydrogen takes place in the cathode (inner compartment) with the simultaneous generation of oxygen ions (eq 1) on the triplephase boundaries (TPB), defined as the region where electrolyte (YSZ), gas, and catalyst (Pt) regions contact. These oxygen ions under the load (positive potential at anode) move from the point of generation to anode through electrolyte (YSZ: O²⁻ ionic conductor), where depending upon the SOEC operation, two competing reactions can take place. In conventional SOEC operation, oxygen evolution reaction is predominant (eq 2) while in plasma-activated SOEC operation, oxygen species can react with activated nitrogen (noted as N_x^*) for the formation of nitric oxides (eq 3). The latter reaction is the key novelty of this contribution. Cathode:

$$2H_2O + 4e^- \rightarrow 2H_2 + 2O^{2-}(YSZ)$$
 (1)

Anode:

Plasma OFF:
$$2O^{2-}(YSZ) + N_2 \rightarrow O_2 + N_2 + 4e^-$$
 (2)

Plasma ON:
$$xO^{2-}(YSZ) + N_x^* \rightarrow xNO + 2xe^-$$
 (3)

Unlike conventional plasma catalysis, which requires the coactivation of reactants, our unique approach ensures that all the energy of the plasma is directed toward activating the nitrogen. Therefore, this "dual chamber" approach has the inherent advantage of separating both the reactants and the most important process steps in space, namely, the activation or dissociation of the base molecules and the formation of products, respectively.

Figure 3 depicts the production rate of NO, O_2 , and H_2 at 650 °C upon step change in the applied current (20 mA) and plasma (80 W) sequentially. In order to perform this experiment under conditions of fixed O^{2-} fluxes, water splitting has been carried out at 20 mA applied current (i.e., galvanostatic mode). NO, O_2 , and H_2 were measured using a quadrupole mass spectrometer. Under open-circuit (I = 0) and



Figure 3. Production rate of NO, O_2 , and H_2 at 650 °C upon sequential step changes of the applied current (20 mA) and the plasma (80 W).

plasma off conditions, no reaction takes place in either compartment. Applying current at t = 10 min (I = 20 mA) in the absence of plasma leads to only water electrolysis, producing hydrogen (~104 nmol H₂/s) and oxygen (~50 nmol O₂/s) in the two chambers. The rate of hydrogen production is double the rate of oxygen production without plasma as stoichiometrically expected, while no NO_x (i.e., NO, NO₂, or N₂O) synthesis has been observed. Thus, there is no electrochemical NO_x synthesis. Upon plasma ignition at t = 20min, NO formation starts taking place with a simultaneous decrease of the oxygen evolution, and a steady state is reached after ~2 min. Rate of NO production (63 nmol NO/s) is roughly double the rate of oxygen consumption (31 nmol O₂/ s), which is consistent with reaction stoichiometry.

Moreover, except NO, no other products such as NO₂ and N₂O were observed throughout the experiment. Once plasma is switched off at t = 35 min, the NO production rate gradually returns to zero, while O₂ formation returns to its initial value. By current interruption at t = 45 min, H₂ and O₂ signals drop to zero. In essence, as shown by this transient experiment, the selective production of NO (63 nmol NO/s) without the formation of other byproducts occurs only in the presence of plasma, verifying that it is clearly a plasma-activated process.

Figure 4a depicts the effect of applied current under plasmaactivated nitrogen on the production rate of NO. Upon current application, oxygen ions arriving on the Pt/YSZ interface are diffused on the catalyst surface as adsorbates, where they can either react with activated nitrogen species for NO formation or with coadsorbed oxygen species for the formation of molecular oxygen. In the low-current range (<20 mA), a linear increase of NO production with the applied current is observed, because the reaction is limited by the supply of oxygen species. In electrochemical cells, the reaction zone is limited in the vicinity of the triple (gas-catalyst-electrolyte) phase boundary. At higher currents, NO formation reaches a saturation value which can be attributed to the limited supply of activated nitrogen species on the TPB area and the higher driving force for oxygen evolution reaction. Both are strongly related to the microstructural properties of the catalyst (plasma electrode), such as porosity, particle size, tortuosity, etc. (Figure S1). This assumption is consistent with the observed faradaic efficiency (i.e., the conversion of oxygen to nitric oxide), which starts from 93% and gradually decreases with increasing current (Figure 4b). The corresponding conversion of nitrogen to nitric oxide is 0.045% at 20 mA.

Although the available experimental data for our hybrid plasma-activated SOEC system do not yet allow for a detailed description of the key species and the involved reaction mechanisms, a straightforward qualitative hypothesis is presented in what follows. In the afterglow of RF nitrogen plasmas (e.g., see ref 17) a relative concentration of 0.1% atomic nitrogen, N, is found. Highly vibrationally excited nitrogen molecules N_2 ($\nu > 13$) and long-living metastable molecules, $N_2(A)$, are a factor of 10 and 10^{-4} less abundant than N. Assuming the same relative concentration of N would lead under the present experimental conditions to a flux of atomic nitrogen species impinging onto surface of the electrochemical cell of ~1.5 \times 10¹⁶ s⁻¹, thereby considering an ideally flat electrode surface. The flux of oxygen ions through the membrane is of the same order of magnitude (<6 \times 10¹⁶ s⁻¹, equivalent to twice the value of 50 nmol/s as reported for 20 mA in Figure 3). At this current level, further NO formation would be hampered by the availability of atomic



Figure 4. (a) Effect of current on the rate of NO, (b) faradaic efficiency of NO production, (c) H_2 production, and (d) Pt/YSZ/Pt cell voltage (black open symbols correspond to normal SOEC operation, whereas orange filled symbols correspond to plasma-activated operation).

nitrogen and the NO formation rate levels off. This qualitative picture still entirely neglects the flux of vibrationally excited nitrogen molecules from the afterglow, recombination of atomic nitrogen species on the surface, and kinetic effects, which will be subject to further research efforts. Nevertheless, especially under the low-pressure conditions in the plasma compartment it is safe to assume that the oxidation of plasmaactivated nitrogen species impinging on the TPB is the key mechanism of NO formation. In the absence of plasma, NO formation has not been observed (Figure 3), which highlights the need of the plasma-activation step.

When the plasma power is changed modestly, the impinging flux of activated nitrogen is modified, which should affect the NO formation rate. In Figure S2 the effect of plasma power on the NO production is shown. At the three examined conditions, a similar behavior is observed; that is, NO production increases in the low-current range followed by a plateau at higher current values. Upon increasing plasma power, more activated nitrogen species are generated and become available at the TPBs, thus leading to higher NO formation rates at the same current levels. The observed behavior of NO formation rates as a function of applied plasma power are consistent with our aforementioned hypothesis about the main reaction mechanisms. Therefore, a detail study of effect of TBP, electrode thickness, and plasma characteristics will be required to further elucidate this point; this will be the topic of a future work.

Interestingly, the amount of NO produced is more than 3 orders of magnitude greater than the equilibrium concentration of the NO in an $N_2/O_2/NO$ mixture at this temperature and concentration (Figure S3, top). Similar levels of NO concentration at equilibrium can be achieved only at

operating temperatures in the range of 1600-1800 °C (Figure S3, bottom).

An important and unique feature of our concept is that apart from nitrogen fixation at the anode, hydrogen is also produced at the cathode as a result of water reduction. The hydrogen production as a function of applied current is shown in Figure 4c. Moreover, because of our reactor configuration, the plasma active area is far from the catalyst, so the SOEC polarization curve (Figure 4d) and the electrochemical impedance spectra (Figure S4) are not affected.

This contribution serves as a proof of principle demonstrating that plasma-activated gas can be implemented in electrochemical systems. The energy consumption in our system is 1350 MJ/N-mol which is within the range of reported values (47 to 2698 MJ/N-mol) for N₂ fixation by H_2O .^{19–22} It should be emphasized that there is plenty of room for improvement by utilizing advanced SOEC catalyst architectures³³ and adjusting operational parameters.

We have demonstrated that surface-generated oxygen by means of a solid oxide electrolyte membrane is reacted with activated nitrogen gas for the first time, paving the way for an innovative all electric nitrogen fixation pathway. It is worthwhile to note that the counterproduct of the electrolysis reaction, i.e., hydrogen, is also a commercially viable compound in addition to being a topic of research for the hydrogen economy.

ASSOCIATED CONTENT

Supporting Information

The Supporting Information is available free of charge on the ACS Publications website at DOI: 10.1021/acsenergy-lett.9b01517.

Experimental methods, microstructural characterization of Pt/YSZ interface, effect of current and plasma power on the NO production, equilibrium concentration of NO as a function of the O₂ concentration at 650 °C, and Nyquist plot of Pt/YSZ/Pt at OCV with and without plasma (PDF)

AUTHOR INFORMATION

Corresponding Author

*E-mail m.tsampas@differ.nl. Phone: +31403334820.

ORCID [©]

Mihalis N. Tsampas: 0000-0002-4367-4457

Author Contributions

[§]H.P. and R.K.S. contributed equally to the article.

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

This project has been cofinanced by TKI-Energie from Toeslag voor Topconsortia voor Kennis en Innovatie (TKI) from the Ministry of Economic Affairs and Climate Policy. The authors thank E. Langereis (DIFFER) and B. Lamers (DIFFER) for help with the illustrations and H. Dzafic (TU.e) for his contribution in completing the setup. ISPT, University of Twente, Nouryon, OCI Nitrogen, Vopak, and Yara are also acknowledged for their support in the project.

REFERENCES

(1) Gur, T. M. Review of electrical energy storage technologies, materials and systems: challenges and prospects for large-scale grid storage. *Energy Environ. Sci.* **2018**, *11*, 2696–2767.

(2) Schiffer, Z. J.; Manthiram, K. Electrification and Decarbonization of the Chemical Industry. *Joule* **2017**, *1*, 10–14.

(3) Kyriakou, V.; Garagounis, I.; Vasileiou, E.; Vourros, A.; Stoukides, M. Progress in the Electrochemical Synthesis of Ammonia. *Catal. Today* **2017**, *286*, 2–13.

(4) Van der Ham, C. J. M.; Koper, M. T. M.; Hetterscheid, D. G. H. Challenges in reduction of dinitrogen by proton and electron transfer. *Chem. Soc. Rev.* **2014**, *43*, 5183–5191.

(5) Liu, H. Ammonia synthesis catalyst 100 years: Practice, enlightenment and challenge. *Chin. J. Catal.* **2014**, *35*, 1619–1640.

(6) Marnellos, G.; Stoukides, M. Ammonia synthesis at atmospheric Pressure. *Science* **1998**, *282*, 98–100.

(7) Patil, B. S.; Wang, Q.; Hessel, V.; Lang, J. Plasma N_2 -fixation: 1900–2014. Catal. *Catal. Today* **2015**, 256, 49–66.

(8) Patil, B. S.; Peeters, F. J. J.; Medrano, J. A.; Gallucci, F.; van Rooij, G.; Lang, J.; Wang, Q.; Hessel, V. Plasma assisted nitrogen oxide production from air: using pulsed powered gliding arc reactor for a containerized plant. *AIChE J.* **2018**, *64*, 526–537.

(9) Opländer, C.; Baschin, M.; van Faassen, E. E.; Born, M.; Möller, M.; Pallua, N.; Suschek, C. V. A new method for sustained generation of ultra-pure nitric oxide-containing gas mixtures via controlled UVA-photolysis of nitrite solutions. *Nitric Oxide* **2010**, *23*, 275–283.

(10) Thengane, S. K.; Bandyopadhyay, S.; Mitra, S.; Bhattacharya, S.; Hoadley, A. An alternative process for nitric oxide and hydrogen production using metal oxides. *Chem. Eng. Res. Des.* **2016**, *112*, 36–45.

(11) Fridman, A. *Plasma Chemistry*; Cambridge University Press, 2008; DOI: 10.1017/CBO9780511546075.

(12) Utz, A. L. Vibrations that live long and prosper. Nat. Chem. 2018, 10, 577-578.

(13) Mehta, P.; Barboun, P.; Go, D. B.; Hicks, J. C.; Schneider, W. F. Catalysis Enabled by Plasma Activation of Strong Chemical Bonds: A Review. *ACS Energy Lett.* **2019**, *4* (5), 1115–1133.

(14) Bogaerts, A.; Neyts, E. C. Plasma Technology: An Emerging Technology for Energy Storage. *ACS Energy Lett.* **2018**, 3 (4), 1013–1027.

(15) Loureiro, J.; Ferreira, C. M. Coupled electron energy and vibrational distribution functions in stationary N2 discharges. *J. Phys. D: Appl. Phys.* **1986**, *19*, 17–35.

(16) Gorse, C.; Cacciatore, M.; Capitelli, M.; De Benedictis, S.; Dilecce, G. Electron energy distribution functions under N2 discharge and post-discharge conditions: a self-consistent approach. *Chem. Phys.* **1988**, *119*, 63–70.

(17) Ricard, A.; Sarrette, J. P.; Jeon, B.; Kim, Y. K. Discharge sourcedependent variation in the densities of active species in the flowing afterglows of N2 RF and UHF plasmas. *Curr. Appl. Phys.* **2017**, *17*, 945–950.

(18) Eyde, S. Oxidation of atmospheric nitrogen and development of resulting industries in Norway. J. Ind. Eng. Chem. **1912**, *4*, 771–774.

(19) Mizukoshi, Y.; Katagiri, R.; Horibe, H.; Hatanaka, S.; Asano, M.; Nishimura, Y. Nitrogen fixation in an aqueous solution by a novel flow plasma system. *Chem. Lett.* **2015**, *44*, 495–496.

(20) Harada, K.; Igari, S.; Takasaki, M.; Shimoyama, A. Reductive fixation of molecular nitrogen by glow discharge against water. *J. Chem. Soc., Chem. Commun.* **1986**, *17*, 1384–1385.

(21) Bian, W.; Shi, J.; Yin, X. Nitrogen fixation into water by pulsed high-voltage discharge. *IEEE Trans. Plasma Sci.* **2009**, 37 (1), 211–218.

(22) Bian, W.; Song, X.; Shi, J.; Yin, X. Nitrogen fixed into HNO₃ by pulsed high voltage discharge. *J. Electrost.* **2012**, *70*, 317–326.

(23) Shmelev, V. M.; Saveliev, A. V.; Kennedy, L. A. Water Purification by Using Microplasma Treatment. *Plasma Chem. Plasma Process.* **2009**, *29*, 275–290.

(24) Whitehead, J. C. Plasma-catalysis: the known knowns, the known unknowns and the unknown unknowns. *J. Phys. D: Appl. Phys.* **2016**, 49 (24), 243001–243024.

(25) Sun, Q.; Zhu, A.; Yang, X.; Niu, J.; Xu, Y. Formation of NOx from N2 and O2 in catalyst-pellet filled dielectric barrier discharges at atmospheric pressure. *Chem. Commun.* **2003**, 1418–1419.

(26) Shah, J.; Wang, W.; Bogaerts, A.; Carreon, M. L. Ammonia synthesis by radio frequency plasma catalysis: revealing the underlying mechanisms. *ACS Applied Energy Materials* **2018**, *1* (9), 4824–4839.

(27) Patil, B. S.; Cherkasov, N.; Lang, J.; Ibhadon, A. O.; Hessel, V.; Wang, Q. Low temperature plasma-catalytic NOx synthesis in a packed DBD reactor: Effect of support materials and supported active metal oxides. *Appl. Catal., B* **2016**, *194*, 123–133.

(28) Li, S.; Medrano Jimenez, J. A.; Hessel, V.; Gallucci, F. Recent progress of plasma-assisted nitrogen fixation research: A review. *Processes* **2018**, *6*, 248–272.

(29) Mehta, P.; Barboun, P.; Herrera, F. A.; Kim, J.; Rumbach, P.; Go, D. B.; Hicks, J. C.; Schneider, W. F. Overcoming ammonia synthesis scaling relations with plasma-enabled catalysis. *Nat. Catal.* **2018**, *1*, 269–275.

(30) Hawtof, R.; Ghosh, S.; Guarr, E.; Xu, C.; Sankaran, R. M.; Renner, J. N. Catalyst-free, highly selective synthesis of ammonia from nitrogen and water by a plasma electrolytic system. *Sci. Adv.* **2019**, *5*, eaat5778.

(31) Kumari, S.; Pishgar, S.; Schwarting, M. E.; Paxton, W. F.; Spurgeon, J. M. Synergistic plasma-assisted electrochemical reduction of nitrogen to ammonia. *Chem. Commun.* **2018**, *54*, 13347–13350.

(32) Triebe, R. W.; Tezel, F. H. Adsorption of nitrogen, carbon monoxide, carbon dioxide and nitric oxide on molecular sieves. *Gas Sep. Purif.* **1995**, *9* (4), 223–230.

(33) Irvine, J. T. S.; Neagu, D.; Verbraeken, M. C.; Chatzichristodoulou, C.; Graves, C.; Mogensen, M. B. Evolution of the electrochemical interface in high-temperature fuel cells and electrolysers. *Nature Energy* **2016**, *1* (1), 15014.